


Standard Colors

H Window Custom Color Options




Black
LT 601*



Quaker Bronze
LT 602*



Beige
LT 603*



Slate Gray
LT 604*



Charcoal Gray
LT 605*




Hartford Green
LT 606*




Sandstone
LT 607*



Boysenberry
LT 608*



Bone White
LT 609*



Military Blue
LT 610*

Special and Exotic Colors

Achieve additional impact and vibrancy.

These products require an additional charge due to the application of a thicker film and/or protective clear coat.



Banner Red
LT 701*



Purple Grandeur
LT 702*



Linetec Blue
LT 703*



Silver
LT 704*



True Yellow
LT 705*



Shannon Green
LT 706*

	AAMA 2603	AAMA 2604	AAMA 2605
South Florida Weathering:			
Color Retention	1yr- "slight" fade	5yrs- Fade = 5 Delta E	10yrs- Fade = 5 Delta E
Chalk Resistance	1yr- "slight" chalk	5yrs- Chalk = 8	10yrs- Chalk = 8
Gloss Retention	No specification	5yrs- 30% retention	10yrs- 50% retention
Erosion Resistance	No specification	5yrs- 10% loss	10yrs- 10% loss
Dry Film Thickness	0.8 mils min.	1.2 mils min.	1.2 mils min.
Pretreatment System	Chrome or Chrome free	Chrome or Chrome free	Chrome = 40mg/sq ft
Accelerated Testing:			
Salt Spray	1,500 hours	3,000 hours	4,000 hours
Humidity	1,500 hours	3,000 hours	4,000 hours
Recommended Paint System*	Baked Enamel	50% Kynar 500™ / Hylar 5000®	70% Kynar 500™ / Hylar 5000®



FINISHER OF CHOICE!™

Linetec • Wausau, WI • Atlanta, GA

linetec.com • sales@linetec.com

800.717.1470 • Fax: 800.226.2500

*Please indicate desired paint system when ordering.
Kynar 500™ is a registered trademark of Atofina Chemicals, Inc. Hylar 5000® is a registered trademark of Solvay Solexis, Inc.
Color samples shown are matched as closely to actual paint color and gloss as reproduction technology allows. Appearance of finish may vary slightly upon factory application. Please contact Linetec for color chip samples.